

The Principle of Valence Bond Amplitude Maximization in Cuprates: How it breeds Superconductivity, Spin and Charge Orders

G. Baskaran
The Institute of Mathematical Sciences
C I T Campus
Madras 600 113, India

A simple microscopic principle of ‘Valence bond (nearest neighbor singlet) amplitude maximization’ (VBAM) is shown to be present in undoped and optimally doped cuprates and unify the very different orderings such as antiferromagnetism in the Mott insulator and the robust superconductivity accompanied by an enhanced charge and stripe correlations in the optimally doped cuprates. VBAM is nearly synonymous with the energy minimization principle. It is implicit in the RVB theory and thereby makes the predictions of RVB mean field theory of superconductivity qualitatively correct.

The qualitative predictions of the RVB mean field theory of high T_c superconductivity [1] in cuprates, including the symmetry of the order parameter [2–5] has turned out to be in good agreement with experiments. In spite of its approximate character it has definitely put us in the correct Hilbert space by focusing on the key singlet correlations. On the other hand various orders, that at a superficial level appear to be unusual from the RVB theory point of view, have emerged both experimentally and theoretically. The aim of the present letter is to identify an unique cause behind the AFM order in the Mott insulator, the enhanced charge and spin stripe correlations and low energy spin fluctuations in the optimally doped superconducting cuprates [6–8]. A simple principle of ‘valence bond (nearest neighbor singlet) amplitude maximization’ (VBAM) is shown to emerge as a fairly simple cause. This maximization respects certain geometrical and dynamic constraint provided by our strongly correlated system. In the case of the Mott insulator, while super exchange interaction respects VBAM, an irreducible amount of local triplet fluctuations is generated in order to satisfy certain geometric constraints. These triplet fluctuations interact and condense at momentum $(\pi, \dots \pi)$ resulting in long range AFM order for any dimension ≥ 2 . In the optimally doped Mott insulator the constraints are modified by the charge dynamics. And VBAM continues as an approximate principle and produces new orders such as the robust superconductivity and the enhanced quasi static charge and spin stripe correlations. We also argue that VBAM is responsible for the qualitative success of the RVB mean field theory.

At a more fundamental level the 2 dimensionality, the one band character, strong correlation and closeness to a Mott insulating state are believed to be responsible for various interesting low energy electronic phenomenon in cuprates [3]. The VBAM hypothesis is an emergent consequence of the above and perhaps an useful guiding principle that at least helps us to separate cause from effects. One of the messages of this letter is that it is VBAM, rather than the development of charge or spin stripe correlations that is providing a mechanism for su-

perconductivity: on the contrary whenever stripes are nurtured it is at the expense of superconductivity [9,10].

Our VBAM hypothesis is proved for the case of undoped Mott insulator by simply using the principle of energy minimization in the ground state. For the optimally doped Mott insulator various arguments are provided in support of this principle. The existence of the sharp 41 meV triplet resonance [11] at (π, π) at optimally doped bilayer YBCO and its counterpart at various dopings all the way up to zero doping is presented as an experimental support for our VBAM hypothesis in the optimally doped regime.

The phase coherent resonance of singlet bonds is at the heart of the RVB theory of superconductivity. Anderson’s RVB wave function [2],

$$|RVB\rangle = P_G \left(\sum a_{ij} b_{ij}^\dagger \right)^{\frac{N_c}{2}} |0\rangle \quad (1)$$

by construction has enhanced VB amplitude. It is a remarkably universal wave function in the sense, it can describe an antiferromagnetically ordered Mott insulating state and the robust superconducting state of the optimally doped Mott insulator with equal ease for appropriate choices of the pair function a_{ij} . We believe that this universal feature is a consequence of the VBAM principle. Also without changing the RVB wave function and consequently the superconducting property in a fundamental fashion, the charge stripe and spin stripe order can be incorporated by a modulation of the pair function a_{ij} .

To begin with we develop a heuristic picture of VBAM. In a free fermi gas, any short range singlet correlation contained in the ground state is a consequence of Pauli principle rather than interactions. In the large U Hubbard model, accepted as a good model for our narrow band conducting cuprates close to half filling, every elementary collision between two electrons tries to establish a nearest neighbor singlet correlations (a valence bond). That is, the virtual transitions to doubly occupied state on a given copper site lowers the energy (compared to the $U = \infty$ case) by the super exchange energy $J \approx \frac{2t^2}{U}$ and

stabilizes the spin singlet state rather than a triplet state. Elementary collisions, in addition to the Pauli principle induce singlet correlations. Close to half filling elementary two body collisions are more frequent than free hopping of charges. *The on site collision induced valence bond proliferation* is at the heart of the VBAM principle.

Let us try to understand the development of long range AFM order in the spin half Mott insulators in the light of the principle of VBAM. In an isolated pair of neighboring orbitals, the electron pair has a spin singlet (non-magnetic) ground state, through the super exchange interaction. An important question is how this local non magnetic singlet tendency manifests itself in a 2 or 3 dimensional lattice. The spin half Heisenberg Hamiltonian with nearest neighbor interaction

$$H = J \sum_{\langle ij \rangle} (\mathbf{S}_i \cdot \mathbf{S}_j - \frac{1}{4}), \quad (2)$$

in terms of the underlying electron variables c 's and the bond singlet operator $b_{ij}^\dagger \equiv \frac{1}{\sqrt{2}}(c_{i\uparrow}^\dagger c_{j\downarrow}^\dagger - c_{i\downarrow}^\dagger c_{j\uparrow}^\dagger)$ takes the form

$$H = -J \sum_{\langle ij \rangle} b_{ij}^\dagger b_{ij}, \quad \text{with } n_{i\uparrow} + n_{i\downarrow} \neq 2 \quad (3)$$

We have used the important identity [4]

$$(\mathbf{S}_i \cdot \mathbf{S}_j - \frac{1}{4}n_i n_j) \equiv b_{ij}^\dagger b_{ij} \quad (4)$$

The singlet number operator $b_{ij}^\dagger b_{ij}$ has an eigen value of 0 or 1 in our single occupancy subspace. In view of the above identity, in a translationally invariant ground state, what is maximized consistent with the lattice structure, is the valence bond amplitude. *Thus in the nearest neighbor Heisenberg models minimization of the ground state energy is synonymous with maximization of the strength of nearest neighbor singlet bonds.* This proves our VBAM hypothesis for the spin half Mott insulator.

Even though diagonal in terms of the number operators $b_{ij}^\dagger b_{ij}$, equation (2) is not really diagonalized, as the number operators themselves do not commute whenever one of the sites coincide:

$$[b_{ij}^\dagger b_{ij}, b_{jk}^\dagger b_{jk}] = i(\mathbf{S}_i \times \mathbf{S}_k) \cdot \mathbf{S}_j \quad (5)$$

This non-commutativity propagates an irreducible minimum of bond triplet fluctuations in the ground state by making the ground state average $\langle b_{ij}^\dagger b_{ij} \rangle_G < 1$. In fact, $\langle b_{ij}^\dagger b_{ij} \rangle_G \approx 0.6391, 0.5846$ and $= 0.5$ respectively for 1d chain, 2d square lattice and infinite d hyper cubic lattice. In the 1d chain the bond triplet fluctuation is finite and manages to produce an algebraic AFM order. In 2d it increases further and is believed to produce a true long range order and in infinite d it increase even further to produce a perfect Neel order. The chiral operator appearing on the right hand side of equation (5) also tells

us that chiral fluctuations are also induced in the ground state.

A long range magnetic order, when it occurs in the ground state, is an inevitable consequence of VBAM in the presence of the constraints provided by the lattice structure and the above commutation relation. Thus in a hyper cubic lattice for $d \geq 2$

VBAM + geometrical constraints $\Rightarrow$ AFM Order

The nature of magnetic order is strongly lattice dependent. For the non bipartite 2d triangular lattice, what maximizes the bond singlet amplitude is a 120° structure with zero point fluctuations. The case of P doped Si in the insulating state is described by a 3d random lattice Heisenberg model. The nature of lattice constraint being very different long range magnetic order is believed to be absent resulting in a kind of singlet bond glass state.

The role of the long range AFM order should not be also overemphasized in this context. As shown by Liang, Docout and Anderson [12], the energy difference between a disordered spin liquid state with only short range AFM correlations and the the best variational state with long range AFM order is as small as one or two percent of the total energy:

$$\frac{\langle b_{ij}^\dagger b_{ij} \rangle_{SL} - \langle b_{ij}^\dagger b_{ij} \rangle_G}{\langle b_{ij}^\dagger b_{ij} \rangle_G} \sim 0.01 \quad (6)$$

At the level of variational wave function a small change in the long distance behavior of the pair function a_{ij} takes us between a disordered and ordered ground state. Hsu [13] also shows that the AFM order in 2d is a spinon density wave in a robust spin liquid state. *Thus the development of long range AFM order in 2d is a result of a small final adjustment of the VB amplitude in a spin liquid state in the maximization procedure.*

We wish to argue that VBAM principle continues to be approximately valid for the optimally doped ($\delta \approx 0.15$) regime and produce, in the presence of the constraints modified by the hole dynamics, the robust superconducting order and also the enhanced charge and spin stripe correlations. The discussion will be heuristic and also uses known results from the RVB theory. We will not consider the under doped regime, as disorder and long range coulomb interaction play important roles and suppress superconductivity strongly and produce mesoscopic phase separation complication.

The t-J model

$$H_{tJ} = -t \sum_{\langle ij \rangle} (c_{i\sigma}^\dagger c_{j\sigma} + h.c.) - J \sum_{\langle ij \rangle} (\mathbf{S}_i \cdot \mathbf{S}_j - \frac{1}{4}n_i n_j),$$

takes the form

$$H_{tJ} = -t \sum_{\langle ij \rangle} (c_{i\sigma}^\dagger c_{j\sigma} + h.c.) - J \sum_{\langle ij \rangle} b_{ij}^\dagger b_{ij} \quad (7)$$

with the usual constraint $n_{i\uparrow} + n_{i\downarrow} \neq 2$. We would like to see if VBAM continues to be valid in the presence of the single electron hopping term in the optimally doped case.

From energy minimization point of view the double occupancy constraint limits the single particle kinetic energy gain per site to $\Delta_{KE} \sim tz\delta$ compared to the larger super exchange energy gain $\Delta_{SE} \sim Jz(1 - \delta^2)$. For cuprates, with a co-ordination number $z = 4$ and $\frac{t}{J} \approx 2$, when $\delta \sim 0.15$ the ratio $\frac{\Delta_{SE}}{\Delta_{KE}} \approx 3$. From the energy considerations given above, the VBAM principle continues to be important in the optimally doped regime. The above rough estimate is in agreement with more accurate estimates using variational monte carlo studies.

The nature of constraints on valence bond proliferation has changed now; we will see how it can stabilize new low temperature phases such as the robust superconductivity along with quasi static charge and spin stripe correlations. Maximizing valence bond amplitude is an important step towards establishing a robust superconducting state. The next important step is the development of ‘in phase resonance’ of the valence bonds (or the zero momentum condensation of the charged valence bonds) in the ground state. This is what is precisely achieved in the RVB mean field theory. In this sense the VBAM principle is satisfied by the RVB mean field theory. While the original RVB mean field theory emphasized the extended-s mean field solution, Kotliar’s identification of $d_{x^2-y^2}$ -wave RVB solution as a lower energy mean field solution made the RVB theory closer to experiments in terms of the symmetry of the order parameter.

After the original RVB mean field theory, and some experimental developments of that time, the inclusion of the on site constraint was suspected to produce a large phase fluctuations and in the even remove the finite temperature K-T transition in an isolated CuO_2 layer. However, recent experiments [14] have strongly supported the one layer d-wave superconductivity with a large $T_c \approx 95K$; in addition the RVB Ginzburg Landau functional derived by Anderson and the present author [15,16], in the RVB gauge theory approach did not show any singular effect on the GL coefficients due to the on site constraints. Very recently Lee [17], using RVB gauge theory has provided a rather convincing non perturbative analysis supporting the *local* stability of the d-wave solution.

What the experiments and also various theoretical clues have been telling us is that the effect of the strong correlation (on site constraint) does affect superconductivity in unexpected fashions by encouraging quasi static charge stripe and spin stripe order. Within the VBAM principle we can understand it in the following heuristic fashion: the super exchange term tries to segregate the holes so that they have more fluctuating Mott insulating region where super exchange gain (or equivalently

the bond singlet amplitude) can be maximized. If the hole segregation has the form of a 1d charge stripes, in addition to VBAM, kinetic energy gain also results from coherent charge delocalization along the charged stripes for the following reason. In view of the Brinkman-Rice phenomenon and proliferation of non self retracing paths in 2d, ‘holes’ can not maximize the kinetic energy gain by coherent delocalization in 2d. The quasi 1d fluctuating stripes on the other hand provides maximum of self retracing paths (along the stripes) for the holes thereby gaining coherent charge delocalization energy.

Since the quasi static charge stripe formation also creates coherently fluctuating Mott insulator region, VBAM leads to enhanced quasi static antiferromagnetic correlations (incommensurate order). Thus charge stripe and spin stripes are intimately related. In the optimally doped region, the development of charge and spin stripe correlations arise from finer adjustments of a robust superconducting state in order to satisfy the VBAM principle. These adjustments can be already done at the level of RVB mean field theory in the following fashion both in the *normal state and superconducting state*: a) development of spontaneous anisotropic valence bond amplitudes [16], $|\Delta_x| \neq |\Delta_y|$ and b) one dimensional spatial modulation of $|\Delta_{ij}|$ either along the x or y axis [18,19].

The first case corresponds to stripes having a orientational order (along the a or b axis) and no spatial order. In the normal state this will be a nematic metal with $\rho_a \neq \rho_b$ and other wise a non fermi liquid state. This state will have an enhanced magnetic correlations around (π, π) , in view of the spin localization caused by the quasi static stripe formation, This anisotropy can continue into the low temperature superconducting phase and will result in a real mixing of $d_{x^2-y^2}$ and extended-S state. Perhaps this phase is already seen [20] in the under doped LSCO - we think that the conducting charge stripe glass state is an anisotropic metallic state (nematic metal). As explained elsewhere [9] coupling to octahedral rotations and displacements in LSCO further enhance the charge stripe correlation at the expense of superconductivity.

The second case corresponds to a spatial ordering of the stripes, which can also start in the normal state, independent of the low temperature superconducting state. Close to the magic filling of $\frac{1}{8}$ this is believed to happen in doped LCO.

In both cases there will be domain formation and the transition from the isotropic metallic phase to the above anisotropic phase can be a second order phase transition. In the optimally doped region, even in the most favorable case of LSCO, the stripe correlations are not stabilized into a true long range order. However, they remain as additional correlations in the ground state there by reducing superconductivity.

At the level of wave function modifications the above secondary stripe orders appear as modifications of the pair function a_{ij} without changing the RVB supercon-

ducting wave function in a fundamental fashion.

We will discuss briefly the question of low energy spin fluctuations in optimally doped cuprates. It is an experimental fact that in the singlet dominated cuprates there are strong low energy spin fluctuation phenomenon in k-space particularly around the (π, π) region. Among them a remarkably neat and unique phenomenon occurs in the bilayer cuprates: in neutron scattering a resolution limited 41 meV peak [11] corresponding to a triplet excitation with momentum centered around (π, π) is seen below the superconducting T_c . These excitations have very little dispersion over a wide momentum interval around (π, π) , suggesting that we can create spin triplet wave packets of size comparable to the lattice parameter as nearly exact eigen excitations. That is, the triplet excitation is predominantly made of nearest neighbor (Eder [21] also has a nearest neighbor triplet bond picture for the triplet resonance) triplet bonds. Availability of large valence bond amplitude is a prerequisite for being able to create this excited state. It tells us that large amplitude valence bond exist in the ground and they can be indeed converted into triplets carrying a momentum of (π, π) and energy of about 41 meV. And 41 meV is the stabilization of bond singlet energy in the superconducting state relative to the normal state. Indeed various authors [22,23] have extracted the superconducting condensation energy from the spectral properties of the 41 meV peak. It should be also mentioned that interlayer pair tunneling adds further stability to the valence bonds in bilayer cuprates there by supporting our VBAM principle.

We suggest that the triplet resonance around (π, π) is what carries the memory of the Mott insulator. It continues to persist as we go to lower dopings in YBCO and the energy of this peak decreases linearly with the corresponding superconducting transition temperature. In a Mott insulator, where the superconducting T_c vanishes, this triplet excitation around (π, π) becomes soft (in view of the existing triplet condensate) and becomes a Goldstone mode of the antiferromagnetic order. This also tells us that the maximization of the valence bond amplitude is easier in a doped Mott insulator than in an undoped one. The hole dynamics in some sense decreases the constraints provided by the lattice, by effectively converting the valence bond operators into more of ‘unconstrained’ bosons.

Thus the various antiferromagnetic fluctuations including the narrow resonance peak tells us about the growing antiferromagnetic correlation in the ground state, arising from the stabilization of the bond singlets. It is in this sense the antiferromagnetic fluctuations are effects of a deep and growing bond singlet tendency, forced by some geometrical and dynamical constraints, rather than some thing that provide cooper pairing at low energies [24]. *Spin fluctuations are effects rather than causes of*

the singlet dominated superconductivity phenomenon.

Thus the maximization of the bond singlet amplitude can be thought of as a driving force behind the various anomalous correlations one sees in cuprates including the robust high T_c superconductivity. The emergent quasi static charge and spin stripe correlations and superconductivity mutually adjust themselves when some parameters such as doping or temperature are changed; they are not to be thought of driving each other. The fundamental driving force is VBAM which is implicit in the RVB theory.

-
- [1] I. J.G. Bednorz, and K.A. Muller, Z. Phys. **B 64**, 189 (1986)
 - [2] P.W. Anderson, Science **235** 1196 (87)
 - [3] P.W. Anderson, The theory of high temperature superconductivity (Princeton University Press, NY, 1996)
 - [4] G. Baskaran, Z. Zou and P.W. Anderson, Sol. State Comm. **63** 973 (87)
 - [5] G. Kotliar, Phys. Rev. **B 37** 3664 (88); I. Affleck and J. B. Marston, Phys. Rev. **B 37** 3774 (88); H. Fukuyama, Prog. Theor. Phys. (Supplement) **108** 287 (92)
 - [6] Zaanen, J and Gunnarsson, O., Phys. Rev. B **46** 7391 - 1394 (1989)
 - [7] V. Emery, S.A. Kivelson and O.Zachar, Phys. Rev. **56** 6120 (1997)
 - [8] J.M. Tranquada et al. Phys. Rev. Lett., **78** 338 (1997); J.M. Tranquada, Proc. of Univ. of Miami Conf. on High- T_c superconductivity (Jan, 1999), cond-mat/9903458; V.J. Emery, S.A. Kivelson and J.M. Tranquada, Proc. Natl. Acad. Sci. (USA), **96** 8814 (99)
 - [9] G. Baskaran, cond-mat/9910161 (to appear in IJMP Letters B, 2000)
 - [10] S.R. White and D.J. Scalapino, Phys. Rev. **B 60** R753 (1999); Phys. Rev. Lett., **84** 3021 (00)
 - [11] H.F. Fong et al., Phys. Rev. Lett., **75** 316 (95)
 - [12] S. Liang, B. Doucot and P.W. Anderson, Phys. Rev. Lett., **61** 365 (1988)
 - [13] T. Hsu, Phys. Rev. **B 41** 11379 (90)
 - [14] K.A. Moler et al., Science **279** 1193 (1998); C. Panagopoulos et al., Phys. Rev. Lett. **79** 2320 (1997)
 - [15] G. Baskaran and P.W. Anderson, Phys. Rev. **B37** 580 (88)
 - [16] M. Drzazga et al., Z. Phys., **B74** 67 (1989);
 - [17] D.H. Lee, Phys. Rev. Lett., **84** 2694 (00)
 - [18] M. Vojta and S. Sachdev, Phys. Rev. Lett., **83** 3916 (99); see also, C. Castellani et al., Phys. Rev. **75** 4650 (1995).
 - [19] J.H. Han et al., cond-mat/0006046
 - [20] A.W. Hunt et al., Phys. Rev. Lett., **82** 4300 (1999);
 - [21] R. Eder, Phys. Rev. **59** 13810 (99)
 - [22] D.J. Scalapino and S.R. White, Phys. Rev. **58** 8222 (98)
 - [23] E. Demler and S.C. Zhang, Nature **396** 733 (98)
 - [24] D. Pines, Phys. Rep. **250** 329 (95)